

Technical Qualities

MULTIFUND is a 100% acrylic, self dilating, water repellent, washable paint that gives an even matt velvet finish, guaranteeing, at the same time, high vapour permeability to the wall, high coverage, low thickness and an optimum yield. Characterized by optimum expansion over the surface, it is indicated on smooth surfaces and is an ideal base for decorative finishes. The product is of the highest quality and conforms to the norm D.I.N 53 778. It has a low odour level, is non-inflammable and is friendly to both humans and the environment.

Ideal Use

Interior walls to be decorated. Base coat for decorative products.

Surface Preparation

Clean the surface, removing any loose material. For crumbly or very absorbent substrates, apply the recommended acrylic fixative CRILUX or NEOFIX by OIKOS. Wait at least 6 hours before painting over. In order to increase the coverage of the cycle use as primer IL PIGMENTATO by OIKOS.

Application method

Apply two coats of MULTIFUND diluted 50% with drinkable water the first, 40% with drinkable water the second, leaving 4 ÷ 6 hours between each coat. MULTIFUND can be applied by roller, brush or spray gun. It is a self dilating product that does not leave roller marks or brush strokes.

Finish

VELDECOR, MULTIDECOR, by OIKOS.

Safety information

The product is free of heavy metals such as lead or chrome. It does not contain toxic solvents, aromatics or chlorides. There is no risk of any dangerous polymerisation. The product is considered to be a non-dangerous substance if used in the technically correct manner. Normal cautionary measures for the handling of water based paints are advised. No special arrangements are required for the storage, movement and transportation of the product; the containers, residue, eventual spilt material should be cleaned up using absorbent inert material such as sand, soil etc. etc. and then disposed of in accordance with the regional and national regulations in force at that time. Transportation must be carried out in accordance with international agreements.

The product

Composition	Acrylic resins in water dispersion, organic and inorganic pigments, additives aimed at helping application and film formation
Specific weight	1.4 Kg/l ±3% (white)
pH	8,5 ÷ 9
Viscosity	20,000 +/-5% CPS Brookfield (RVT 20 revs/min. a 25°C)
Storage temperature	2°C ÷ +36°C. (Keep from freezing)
Reaction to fire	Negative if the product is applied on a non inflammable base; water based material with dry thickness of less than 0,600mm
Water vapour permeability (Sd)	0.2 m (max allowed limit 2 m DIN 52 615)
Washed resistance	Conforms to the norm DIN 53 778, resistant to at least 1,000 abrasive cycles
Abrasion resistance	Conforms to the norm DIN 53 778, resistant to more than 5,000 abrasive cycles, in this case over 40,000 hits of brush
Cleanness effect	Conforms to the norm DIN 53 778, cleaning of impurities and dirt with less than 800 abrasive cycles
Emission limits of Volatile Organic Compounds (VOC) according to directive 2004/42/CE	<ul style="list-style-type: none"> • Classification: A/a • VOC: 20g/l (max) • Limit Phase I (from 1.1.2007), 75g/l • Limit Phase II (from 1.1.2010): 30g/l
Colours	White + colour chart, from DCS Decor Color System by OIKOS.
Packaging	Liters - 1 - 4 - 10

The application

Dilution	50% the first coat, 40% the second coat, with drinkable water
Yield	14-16 m ² /l in two coats
Application tools	Brush, roller or spray gun (1.7mm nozzle)
Primers	CRILUX, NEOFIX, IL PIGMENTATO by OIKOS
Application temperature	+5°C ÷ +36°C (with relative humidity not exceeding 80%)
Drying time - tack free	1 - 1,30 h (temperature = 20°C with relative humidity around 75%)
Drying time - fully cured	4 days (temperature = 20°C with relative humidity around 75%)
Tools cleaning	Water

Specifications

Clean the surface, removing any loose material. For crumbly or very absorbent substrates, apply an acrylic fixative as CRILUX or NEOFIX by OIKOS.. In order to increase the coverage of the cycle use as primer IL PIGMENTATO by OIKOS. Wait at least 6 hours before painting. Apply then

two coats of an acrylic paint like MULTIFUND by OIKOS, conforming to DIN 53 778, protective, unalterable, washable, and water-repellent. All must be carried out in accordance with the norms of application, at a cost of m². inclusive of materials and labour.