

Technical Qualities

AUREUM by Oikos, regal alchemy, gold for walls, a decorative, golden finish created using lime putty and golden powders with a low environmental impact. The shades of AUREUM derive from the colours of the earth and the warm tones of nature; combining elements from historical research and an understanding of contemporary technology, it has been possible to give rise to a product that is able to adapt itself to both modern and traditional settings. The product makes it possible to achieve precious and elegant finishes in various golden tones, creating, according to the sources of light and the angle at which the surface is looked at, lavish patterns on a golden texture; furthermore, the vivaciousness of the golden reflections, lights up the wall, giving the setting an unmistakable elegance with a silky sensation to the touch. The product is non inflammable and friendly to both humans and the environment.

Ideal Use

Decoration of interior walls and furnishings.

Surface Preparation

Clean the surface to be decorated, removing any loose or flaking material. Apply a coat of the fixative IL PRIMER by OIKOS in order to insure perfect adhesion. Screed the surface with STUCCO IN PASTA PER RASATURA by Oikos.

Application Method

For an impeccable finish, apply AUREUM in two coats using the special Inox steel trowel by Oikos (art.113) if necessary it is possible to add up to a maximum of 5% water to the product in order to obtain the right fluidity:

- **first coat:** proceed to spread a thin coat of AUREUM directly on the STUCCO IN PASTA PER RASATURA, making large trowel marks to completely cover the surface. Wait 6 ÷ 8 hours until dry;
- **finish:** apply a very thin coat of product, partially overlapping the trowel marks and gently smoothing the surface with the blade of the trowel; after approximately one hour, pass over the surface for a final time to fully smooth the finish.

Finish

To enhance the gloss effect and protect it, apply after 6 ÷ 8 hours CERA STUCCO by OIKOS.

In order to obtain a higher level of water resistance and washability, apply after 4 ÷ 5 days PROTETTIVO PER STUCCO E MARMORINO by OIKOS.

Specifications

Carefully clean the surface removing any loose or flaking material. Apply a primer or fixative such as IL PRIMER by Oikos in order to insure a perfect adhesion to the surface. Screed over with STUCCO IN PASTA PER RASATURA by Oikos. Apply two coats of a product such as AUREUM by Oikos. The application must be made by trowel. All must be carried out in accordance with the norms of application and with a cost of..... per m² including material and application.

The product

Composition	Lime putty, golden pigments, natural additives, inorganic pigments based on iron oxide
Specific weight	1,2 kg/l ±3%
pH	12 ÷13
Viscosity	Tixotropic paste
Storage temperature	+2°C ÷ +36°C. (Keep from freezing)
Reaction to fire	Negative if the product is applied on a non inflammable base; water based material with a dry thickness of less than 0,600mm
Water absorption W ₂₄	<ul style="list-style-type: none"> • Low • W₂₄: 0,032 kg/m²/t^{1/2} (UNI EN 1062-3:2001)
Permeability to water vapour Sd	<ul style="list-style-type: none"> • High • Sd: 0,0002 m (UNI EN ISO 7783-2:2001)
Emission limits of Volatile Organic Compounds (VOC) according to directive 2004/42/CE	<ul style="list-style-type: none"> • Classification A/I • VOC: 60g/l (max) • Limit Phase I (from 1.1.2007): 300g/l • Limit Phase II (from 1.1.2010): 200g/l
Colours	Shades of the color chart
Packaging	Kg 1 – 5
Warning	<ul style="list-style-type: none"> • Avoid prolonged contact with the skin: if necessary, wash thoroughly with soap and water. If the irritation persists, consult a doctor • Avoid contact with the eyes, in case of accidental contact, wash thoroughly with a sugar-water solution. If the irritation persists, consult a doctor

The application

Dilution	ready to use, max 5% water
Indicative yield	5 ÷ 6 m ² /kg
Application tools	Inox steel trowel by Oikos
Fixative	IL PRIMER by Oikos
Base coat	STUCCO IN PASTA PER RASATURA by Oikos
Protection	CERA PER STUCCO, PROTETTIVO PER STUCCO E MARMORINO by OIKOS
Application temperature	+5°C ÷ +36°C (with relative humidity not exceeding 80%)
Tack free time	1 h (temperature = 20°C with relative humidity at 75%)
Total drying time	20 ÷ 25 days (temperature = 20°C with relative humidity at 75%)
Tools cleaning	Water

Safety information

The product is free of heavy metals such as lead or chrome. It does not contain toxic solvents, aromatics or chlorides. There is no risk of any dangerous polymerisation. The product is classified as hazardous pursuant to the provisions set forth in the Regulations (CE) 1272/2008 (CLP) and subsequent amendments and supplements. For further information see the product Safety Data Sheet. Normal cautionary measures for the handling of water based

paints are advised. No special arrangements are required for the storage, movement and transportation of the product; the containers, residue, eventual spilt material should be cleaned up using absorbent inert material such as sand, soil etc. etc. and then disposed of in accordance with the regional and national regulations in force at that time. Transportation must be carried out in accordance with international agreements.